



# VeroClear

## POLYJET TECHNOLOGY MATERIAL SPECIFICATIONS

### Highlights

- Transparent, rigid and accurate
- High dimensional stability
- Produces excellent fine feature detail
- Quickly and economically produces parts
- Available in two Z resolutions
  - PolyJet: 30µm (0.00118")
  - PolyJet HD: 16µm (0.00063")

### Applications

- Highly accurate presentation models
- Smaller parts with complex features
- Clear medical devices, casings and components for unique reveals
- Transparent electronic housings
- Suitable for a wide range of industries

## TYPICAL PHYSICAL PROPERTIES

MECHANICAL PROPERTIES	TEST METHOD	ENGLISH	METRIC
<b>Color/Appearance</b>	Visual	Transparent	Transparent
<b>Tensile Strength</b>	ASTM D638	7,250 - 9,450 psi	50-65 MPa
<b>Elongation at Break</b>	ASTM D638	10% - 25%	10% - 25%
<b>Modulus of Elasticity</b>	ASTM D638	290,000 - 435,000 psi	2,000 - 3,000 MPa
<b>Flexural Strength</b>	ASTM D790	11,000 - 16,000 psi	75 - 110 MPa
<b>Flexural Modulus</b>	ASTM D790	320,000 - 465,000 psi	2,200 - 3,200 MPa
<b>Izod Notched Impact</b>	ASTM D256	0.375 - 0.562 ft-lb/in	20 - 30 J/m
<b>Shore D Hardness</b>	-	83 - 86 D	83 - 86 D
<b>Heat Deflection Temperature</b>	ASTM D648 @ 264 psi	113 - 122°F	45 - 50°C
	@ 66 psi	113 - 122°F	45 - 50°C

The information presented represents typical values intended for reference and comparison purposes only. It should not be used for design specifications or quality control purposes. End-use material performance can be impacted (+/-) by, but not limited to, part design, end-use conditions, test conditions, color etc. Actual values will vary with build conditions. Product specifications are subject to change without notice.

The performance characteristics of these materials may vary according to application, operating conditions, or end use. Each user is responsible for determining that the material is safe, lawful, and technically suitable for the intended application. StratasyS makes no warranties of any kind, express or implied, including, but not limited to, the warranties of merchantability, fitness for a particular use, or warranty against patent infringement.

